

Product Description

ORALITE® retroreflective films series 5910 High Intensity Prismatic Grade are highly reflective, weatherproof, self-adhesive films with excellent corrosion and solvent resistance. The product was specifically developed for the manufacture of traffic control, guidance, warning and information signs, which are intended for long term vertical outdoor use.

ORALITE® 5910 sheeting is composed of a UV stabilized acrylic front film. Its retroreflective system consists of sealed cells of air backed microprisms, using total internal reflection. The distinct shape of the sealing pattern identifies the machine direction and the manufacturer of the sheeting shown in Figure 1. The sheeting displays a watermark with the product number & durability in years in a repeat pattern to provide identification to users & visual verification of proper use by inspectors, shown in Figure 2.

The product complies with the requirements of EN 12899-1:2007 Clause 4.2 concerning microprismatic materials and has been granted a European Technical Approval (ETA No. 12/0478) exceeding the minimum coefficient of retroreflection for performance Class R2.

Retroreflectivity

ORALITE® 5910 exceeds the minimum performance requirements of CUAP class R2, DIN 67520:2008-11 (RA2; design C) and ASTM D4956-11a (Type IV sheeting). The required minimum retroreflection values, shown in tables 1 and 2, are complied with when measured in accordance with the corresponding specifications using CIE standard illuminant A, and the provisions of CIE No.54.2.

Color

ORALITE® 5910 High Intensity Prismatic Grade sheeting is available in white (010), yellow (020), orange (035), red (030), green (060), blue (050) and brown (080). The sheeting conforms to the daytime color requirements in tables 3 & 4 when measured in accordance with the corresponding specifications, the provisions of CIE No. 15.2, & shall comply with the specifications of DIN 6171: 2003-08 & ASTM D4956-11a.

Figure 1 - Sealing pattern and application directions




Figure 2 - Watermark

OR 5910
10 Years

Adhesive

The adhesive consists of a solvent polyacrylate, permanent pressure sensitive adhesive specially formulated for the application to metallic surfaces such as aluminium and zinc coated steel plate. The adhesive is protected by a release liner made of polypropylene film, silicone coated on one side, 0.075 mm [0.003"] thickness.

Application/Processing

ORALITE® 5910 High Intensity Prismatic Grade was especially developed for traffic control applications. Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. For other applications the user is fully responsible for evaluating the suitability of the product, and for any risks associated with that use.

ORALITE® 5910 in white color can be screen or digitally printed or laminated with overlay films. The printed or laminated sheeting will continue to meet the retroreflective values of the respective color provided that ORAFOL's application guidelines are followed. The overlay films recommended are: ORALITE® 5061 Transparent film, ORALITE® 5090 Anti Dew film and ORALITE® 5095 Anti Graffiti film. The screen printing ink recommended is ORALITE® 5018. A transparent coating is not necessary.

The material can also be printed on the ORALITE® UV Digital Sign Printer with the specially developed UV digital inks ORALITE® 5019. For long term vertical outdoor use, the printed material should be used in combination with ORALITE® 5061 Transparent film.

Please refer to the Practical Information #4.3 published by Orafol for full instructions or contact your ORAFOL Reflective Solutions Division representative for advice relating to the above.

Note: All ORALITE® products are manufactured within an ISO 9001:2008 controlled manufacturing environment and batch traceability is possible on the basis of the roll number.

Product Data

Retroreflectivity for new sheeting (cd/lx/m²) as per CUAP Table 7 Class R2, DIN 67520:2008-11 and ASTM D4956-11a:

Observation angle	0.2°			0.33°			2°		
	5°	30°	40°	5°	30°	40°	5°	30°	40°
white	250	150	110	180	100	95	5	2.5	1.5
yellow	170	100	70	122	70	64	3	1.5	1
orange	100	60	29	65	40	20	1.5	1.0	#
red	45	25	15	25	14	13	1.0	0.4	0.3
green	45	25	12	21	12	11	0.5	0.3	0.2
blue	20	11	8	14	8	7	0.2	#	#
brown	12	8.5	5	8	5	3	0.2	#	#

Observation angle	0.1°		0.2°		0.5°	
	-4°	30°	-4°	30°	-4°	30°
white	500	240	360	170	150	72
yellow	380	175	270	135	110	54
orange	200	94	145	68	60	28
red	90	42	65	30	27	13
green	70	32	50	25	21	10
blue	42	20	30	14	13	6
brown	25	12	18	8.5	7.5	3.5

Daytime color specification limits for new sheeting:

Table 3 – Chromaticity coordinates (DIN 6171: 2003-08)									
Colors	1		2		3		4		Luminance Factor β
	x	y	x	y	x	y	x	y	
white	0.305	0.315	0.335	0.345	0.325	0.355	0.295	0.325	> 0.27
yellow	0.494	0.505	0.470	0.480	0.513	0.437	0.545	0.454	> 0.16
orange	0.610	0.390	0.535	0.375	0.506	0.404	0.570	0.429	≥ 0.14
red	0.735	0.265	0.700	0.250	0.610	0.340	0.660	0.340	≥ 0.03
green	0.110	0.415	0.170	0.415	0.170	0.500	0.110	0.500	≥ 0.03
blue	0.130	0.090	0.160	0.090	0.160	0.140	0.130	0.140	≥ 0.01
brown	0.455	0.397	0.523	0.429	0.479	0.373	0.558	0.394	0.03 – 0.09

Table 4 – Chromaticity coordinates (ASTM D4956)									
Colors	1		2		3		4		Luminance Factor (Y %)
	x	y	x	y	x	y	x	y	
white	0.303	0.300	0.368	0.366	0.340	0.393	0.274	0.329	> 27
yellow	0.498	0.412	0.557	0.442	0.479	0.520	0.438	0.472	$15 \leq Y \leq 45$
orange	0.558	0.352	0.636	0.364	0.570	0.429	0.506	0.404	$10 \leq Y \leq 30$
red	0.648	0.351	0.735	0.265	0.629	0.281	0.565	0.346	$2.5 \leq Y \leq 15$
green	0.026	0.399	0.166	0.364	0.286	0.446	0.207	0.771	$3 \leq Y \leq 12$
blue	0.140	0.035	0.244	0.210	0.190	0.255	0.065	0.216	$1 \leq Y \leq 10$
brown	0.430	0.340	0.610	0.390	0.550	0.450	0.430	0.390	$1 \leq Y \leq 9$

Physical and Chemical Properties

Thickness* (without protective paper and adhesive)	0.230 mm (9mils)
Temperature resistance	adhered to aluminium, -56°C to +82°C (-70°F to 180°F)
Resistance to cleaning agents	adhered to aluminium, 8h in solution (0.5% household agents) at room temperature and 65°C (150°F), no variation
Adhesive power**¹ (FINAT-TMI after 24h, stainless steel)	15 N/25mm (1 inch) (film tear)
Shelf life***	1 year
Application temperature	> +10°C (50°F)
Service life by specialist application** under vertical outdoor exposure	10 years (not printed)

* average ** standard central European climate *** in original packaging, at 20°C and 50% relative humidity ¹ 180° Peel @ 300mm (12") /min

Note: Values stated in SI units are to be regarded as standard. The values in parentheses are conversions and shall not be considered as the standard, as these values maybe approximate.



IMPORTANT NOTICE

When using ORALITE® sheeting the relevant national specifications have to be complied with. ORAFOL recommends you obtain the current requirements from your local authority and ensure product conformance with such requirements. Please contact ORAFOL for further information.

All Reflexite® and ORALITE® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning Reflexite® and ORALITE® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of Reflexite and ORALITE® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

No warranty is given for purposes other than those listed in the Technical Datasheet or which are not processed according to ORAFOL's processing and handling instructions. The durability of the signs will depend on a variety of factors, including but not limited to substrate selection and preparation, compliance with recommended application guidelines, geographic area, exposure conditions and maintenance of the product and finished sign. Sign failures caused by the substrate or improper surface preparations are not the responsibility of ORAFOL. Please refer to the full warranty document available at www.orafol.com for detailed information.

ORALITE® is a trademark of ORAFOL Europe GmbH.